

# Primary Lithium Battery CP223830

3.0V [Li-MnO<sub>2</sub>]



### **BENEFITS**

- High Voltage Response, Stable During Most of the Lifetime of the Application
- Energy Density up to 830Wh/L
- Wide Operating Temperature Range (-40 °C ~+70 °C)
- Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25 C)

#### **KEY FEATURES**

- Optimized Battery Structure, Full Discharge Capacity
- Long Endurance
- No Passivation
- GB 8897.4-2008 \ IEC 60086.4:2014 and RoHS

# **MAIN APPLICATIONS**

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

# **References Data**

#### Electrical characteristics

Open circuit voltage (at 23±2°C)

≥3.10V

#### **Nominal capacity**

400mAh

(At +25°C,battery discharged at continuous current 1mA until voltage reaches cut-off voltage 2.0V. The capacity can vary at different temperature, discharge current or cut-off voltage.)

#### Maximum continuous current

100mA

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity.)

# Maximum pulse discharge current 150mA

(At  $+25^{\circ}$ C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. The discharged capacity may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions, consult HCB.)

## Storage (recommended)

≤+30°C

(For more severe conditions, consult HCB)

≤75%RH

#### **Operating temperature range**

-40°C~+70°C

(Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses, consult HCB.)

#### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040

Tel: +86(0)27 83248452

Fax: +86(0)27 83248455

Email: haocheng@cnhcb.com

Web: www.cnhcb.com

No.: HCB-MKT.PM-S[V2.0 2018 02]




# Primary Lithium Battery CP223830

3.0V [Li-MnO<sub>2</sub>]

Physical characteristics	
Width	37.0±1.5mm
Height	30.0±1.0mm
Thickness	2.4±0.2mm
Typical weight	3.5g
Li metal content	0.13g

MSDS as per request Diode (1N4007, 1N5819) PTC (SRS175...)


Tag, wire, connector, etc. available



Dimensions in mm (GB1804-m)

# **WARNING:**


- Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
- Do Not Crush
- Do Not Dismantle
- Do Not Incinerate
- Do Not Mix New and Used Batteries
- Do Not Heat Above 100°C




2.Typical discharge profiles with different current (at discharge stable phase)

Capacity(mAh)

320



# 3.Storage characteristics



### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040

Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com

No.: HCB-MKT.PM-S[V2.0 2018 02]