

# Primary Lithium Battery CP263840

3.0V [Li-MnO<sub>2</sub>]

## - HCB 1802 CP263840 + 3.0V 700mAh

#### **BENEFITS**

- High Voltage Response, Stable During Most of the Lifetime of the Application
- Energy Density up to 830Wh/L
- Wide Operating Temperature Range (-40 °C ~+70 °C)
- Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25°C)

#### **KEY FEATURES**

- Optimized Battery Structure, Full Discharge Capacity
- Long Endurance
- No Passivation
- GB 8897.4-2008、IEC 60086.4:2014 and RoHS

#### **MAIN APPLICATIONS**

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

#### **References Data**

#### **Electrical characteristics**

Open circuit voltage (at +25°C) ≥3.10V

#### Nominal capacity

700mAh

(At +25°C, battery discharged at continuous current 5mA until voltage reaches cut-off voltage 2.0V. The capacity can vary at different temperature, discharge current or cut-off voltage.)

#### **Maximum continuous current**

300mA

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity.)

#### Maximum pulse discharge current 500mA

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. The discharged capacity may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions, consult HCB.)

#### Storage (recommended)

≤+30°C

(For more severe conditions, consult HCB)

≤75%RH

#### Operating temperature range

-40°C~+70°C

(Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses, consult HCB.)

#### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040

Tel: +86(0)27 83248452

Fax: +86(0)27 83248455

Email: haocheng@cnhcb.com Web: www.cnhcb.com

No.: HCB-MKT.PM-S[V2.0 2018 02]




## Primary Lithium Battery CP263840

3.0V [Li-MnO<sub>2</sub>]

Physical characteristics	
Width	38.0±1.0mm
Height	40.0±1.0mm
Thickness	2.7±0.1mm
Typical weight	7.0g
Li metal content	0.33g

MSDS as per request Diode (1N4007, 1N5819) PTC (SRS175...)

Tag, wire, connector, etc. available




Dimensions in mm (GB1804-m)


#### **WARNING:**

- · Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
- Do Not Crush
- Do Not Dismantle
- Do Not Incinerate
- Do Not Mix New and Used Batteries
- Do Not Heat Above 100°C


### 1.Typical discharge profiles at 23±2°C (at mid-discharge)



### 2. Typical discharge profiles with different current (at discharge stable phase)



#### 3.Storage characteristics



#### HCB BATTERY CO., LTD

P.O.: 430040

Tel: +86(0)27 83248452

Fax: +86(0)27 83248455

Email: haocheng@cnhcb.com

Web: www.cnhcb.com

No.: HCB-MKT.PM-S[V2.0 2018 02]